



Applied Technologies, Inc.
601 Jeffers Circle
Exton, PA 19341-2525
(610) 363-9640 Fax: (610) 363-8995

ENGINEERING DATA SHEET
ACRYLIC INSULATOR 3310

3310 is a highly adherent modified acrylic coating used for electronic circuit and component protection. This material may be applied by brushing, banding, dipping, or through automatic dispensing equipment. When properly cured, this product yields a chemically inert film which helps to prevent the effects of corrosion, moisture, oxidation, abrasion, and thermal shock. No ingredients that are corrosive or harmful to electronic components are used in this material. The material is toluene free and has a drying rate which is identical to our 3300 insulator. It meets the requirements for MIL-I-46058C and is available as a fluorescent system for detection under UV light.

COMPOSITION PROPERTIES:

Color***	Transparent Green, Blue, or Clear (see below)
Viscosity	225-325 cps (Brookfield LVT, Spin #2, 12 rpm, 25°C)
Specific Gravity	0.9 g/cc
Cure Schedule	10-15 minutes @ 60-100°C or 24 hours @ 25°C
Service Temperature	-55 to 125°C
Dielectric Breakdown	>1,500 volts/mil
Insulation Resistance	>1 x 10 ¹²
Flexibility	Excellent (No cracking in bend over 1/8" mandrel)
Thinner*	Propyl Acetate
Shelf Life	One year @ 25°C (Sealed Container)

* 3310 is optimized for brushing/banding applications and thinning is not normally necessary. However, propyl acetate may be added, with thorough blending, to replace solvent loss or to make slight adjustments for ease of application. In handling and using organic solvents, the safety precautions recommended in the MSDS should be observed.

** Screen printable versions are available upon request.

*** Opaque Black and White also available upon request.

PROCESSING PARAMETERS:

Surface Preparations	Be sure that all surfaces to be coated with 3310 are clean, dry, and free of any grease or oil.
Mixing	The material should be thoroughly stirred or shaken prior to use.
Application	Material is typically applied by brushing, banding, or dipping. Wet films should be allowed to air dry for one hour prior to handling or recoating.
Curing	Excellent results have been obtained by convection curing for 10 minutes @ 90°C. Optimum cure cycles using radiant or convection conveyer ovens are best determined experimentally. Satisfactory results have also been found in some applications with a 24 hour air dry cure @ 25°C.
Cleanup	Use Acetone, MEK, or Aromatic Hydrocarbon solvents.

The information given herein is based on data believed to be reliable, but Applied Technologies, Incorporated makes no warranties express or implied as to its accuracy and assumes no liability arising out of its use by others or any patent infringement resulting from its use.